



Polymer-Modified Bitumen Emulsions: Production Technology And Application In The Road Construction

Murodov Javlonbek Zafar O'G'Li

Assistant Lecturer, Bukhara State Technical University, Uzbekistan

Haydarov Axtam Amonovich

Professor, Bukhara State Technical University, Uzbekistan

ABSTRACT

This study addresses the production technology and industrial application of polymer-modified bitumen emulsions (PMBE), which combine the environmental and economic advantages of cold-applied bitumen emulsions with the enhanced mechanical performance provided by polymer modification. Two principal manufacturing routes are compared: post-addition of a polymer latex (most commonly styrene-butadiene rubber, SBR) to a finished cationic bitumen emulsion, and pre-blending of the polymer (such as styrene-butadiene-styrene, SBS) into the bitumen prior to emulsification. The influence of polymer type, dosage, and compatibility on emulsion viscosity, storage stability, elastic recovery, and residual binder cohesion is analyzed. Industrial applications reviewed include surface dressing, slurry seal and micro-surfacing, tack coats for high-stress interlayers, and cold in-place recycling, where the elastomeric network formed by the polymer improves resistance to rutting, thermal cracking, and moisture damage. The findings indicate that careful matching of polymer chemistry to the base bitumen and emulsifier system is essential to avoid phase separation and to achieve the full performance benefit of modification.

KEYWORDS: Polymer-modified bitumen emulsion, PMBE, SBR latex, SBS, elastic recovery, storage stability, surface dressing, micro-surfacing, cold in-place recycling, residual binder.

INTRODUCTION

Unmodified bitumen emulsions, while offering clear environmental and energy advantages over hot mix asphalt, produce a residual binder film whose mechanical properties are limited to those of the base bitumen. In regions subject to heavy traffic loading, large temperature fluctuations, or aggressive freeze-thaw cycles, this residual film is prone to rutting at high service temperatures and to cracking at low temperatures. Polymer modification of bitumen emulsions has therefore become an established strategy for extending the service life of cold-applied and surface-treatment technologies, by embedding an elastomeric polymer network within the bituminous binder that is reconstituted after the emulsion breaks.

Two production technologies are used industrially to incorporate polymer into bitumen emulsions. The first, post-addition, involves blending a pre-formed polymer latex — typically an anionic or cationic SBR latex — directly into a finished bitumen emulsion under low-shear mixing after the emulsification step. This route is simpler and requires no modification of the emulsification plant, but the compatibility between the latex charge and the emulsion's own ionic character must be carefully matched to prevent premature coagulation. The second technology, pre-blending, disperses the polymer (commonly SBS block copolymer, though EVA

and other elastomers are also used) into the hot bitumen before it enters the colloid mill, producing a polymer-modified bitumen (PMB) that is then emulsified in the conventional manner. Pre-blending generally yields a more homogeneous residual binder and superior elastic recovery, but requires higher-shear processing equipment and closer temperature control to avoid polymer degradation.

The dosage of polymer, typically ranging from 2 to 5 percent by mass of the bitumen for SBR latex and from 3 to 6 percent for SBS, exerts a strong influence on emulsion viscosity and storage stability. Excessive polymer content increases emulsion viscosity beyond practical spraying or mixing limits and can promote sedimentation or creaming during storage, while insufficient content fails to achieve a continuous elastomeric network in the residual film. Elastic recovery of the residual binder, measured by the ductilometer torsion recovery test, is widely used as a quality indicator: values above 50 percent are generally sought for surface dressing and micro-surfacing applications subject to significant traffic-induced strain.

In industrial practice, polymer-modified bitumen emulsions are applied across several road maintenance and construction technologies. In surface dressing, PMBE provides improved aggregate retention and resistance to traffic-induced stone loss immediately after application. In slurry seal and micro-surfacing systems, the polymer improves the cohesion and rut resistance of the thin wearing course under heavy channelized traffic. As a tack coat between pavement layers, polymer-modified emulsions provide stronger interlayer bonding, reducing the risk of delamination under shear stress. In cold in-place recycling, incorporating a polymer-modified emulsifier system alongside active mineral fillers has been shown to accelerate early strength gain while preserving the flexibility needed to resist reflective cracking.

Overall, polymer modification substantially broadens the performance envelope of bitumen emulsions, allowing cold-applied and surface-treatment technologies to be used with confidence in demanding traffic and climatic conditions. The selection between post-addition and pre-blending routes, and the choice of polymer type and dosage, should be guided by the specific application, the base bitumen source, and the compatibility of the polymer with the emulsifier system. Continued research into polymer-emulsifier compatibility and long-term field performance monitoring is recommended to further optimize formulation guidelines for practical road construction.

References

1. Yildirim, Y. (2007). Polymer modified asphalt binders. *Construction and Building Materials*, Vol. 21, No. 1, pp. 66–72.
2. Lesueur, D. (2009). The colloidal structure of bitumen: Consequences on the rheology and on the mechanisms of bitumen modification. *Advances in Colloid and Interface Science*, Vol. 145, pp. 42–82.
3. Whiteoak, D. (2003). *The Shell Bitumen Handbook*. 5th edition. Thomas Telford Publishing, London.
4. James, A. (2006). Overview of asphalt emulsion. *Asphalt Emulsion Technology*, Transportation Research Circular E-C102, Transportation Research Board, Washington, D.C.